

# SCHEDA TECNICA N°42

# **ANTISALMASTRO A**

## DESCRIPTION

ANTISALMASTRO A is an acrylic product which provides an effective barrier against efflorescence.

Furthermore the raw materials and their reaction to pulverization caused by efflorescence, clearly contribute to extend the paint durability besides the cleaning of the treated surfaces.

ANTISALMASTRO A prevents the salt powders formation, giving a pleasant clean apperance to the treated environment.

## APPLICATION

-The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time, depending on temperature.

- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster.

- Level out imperfections of the internal support with STUCCO TRE STELLE (check technical data sheet n° 33) and the external ones with ESTERN STUCCO (check technical data sheet n°76).

- Use the sandpaper in order to remove surface irregularities and then eliminate dust deposits.

- Make sure the surface is dry and apply 1 coat of ANTISALMASTRO A with brush or roller, which has to be thinned up with water in the following percentages: approx. 5-10%.



COLORIFICIO RIVEDIL di COSIMO CODARDO Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy Tel. (+39) 0832 731293 - (+39) 0832 731273 P.IVA 01122590753 www.rivedil.com - export@rivedil.com

TECHNICAL DATA	
Nature of the bond	N/A
Viscosity	
Drying Time	2 h at touch, 6-12 h complete.
Thinning	Water 5-10%
Yield	4-5m²/Lt
Specific weight	1,057Kg/Lt
Colors	
Dry aspect	
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
voc	μGr/m³
тиос	N/A
РН	N/A
Cleaning	Water
Packing	2,5LT,0,750LT
CHARACTERISTICS	
Characteristics:	Isolante.
Can be applied on:	Walls,Wood.
for:	Interiors ed Exteriors.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Roller,Brush.
Related products:	ESTERN STUCCO, STUCCO 3 STELLE.

#### SAFETY INSTRUCTIONS

The product does not require labelling under the Decree 285 of 16/7/98 and subsequent amendments and updates.

Use the product in accordance with the relevant health and safety regulations of the country. Do not dispose of the containers in the environment after use; let the residues dry and treat them as special waste. For further information please refer to **SSR42** safety data sheet.

#### **ITEM SPECIFICATION**

### NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.

- In the original, sealed containers and in appropriate temperature conditions. The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.

- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge, however, being elements such as weather conditions, labor, tools, quality of third party products and others, not under the direct control of the Rivedil, this document does not constitute a warranty, nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document. We recommend that you always check the suitability of the product to each specific instance. This supersedes all previous editions.



COLORIFICIO RIVEDIL di COSIMO CODARDO Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy Tel. (+39) 0832 731293 - (+39) 0832 731273 P.IVA 01122590753 www.rivedil.com - export@rivedil.com