

SCHEDA TECNICA N°712

HSAN A NATURE SEMIGLOSS

Acrylic paint with a semigloss effect for interior and exterior

DESCRIPTION

H SAN A NATURE SEMIGLOSS is an acrylic, sanitizer paint, semi gloss effect and anti-mold properties.

It is recommended for environments where a high standard of hygiene is required such as: hospitals, schools, restaurants, etc. ...

Moreover, the product has been specifically designed for professional use.

Approved with test report n. 322074 of 'Istituto Giordano'

APPLICATION

New Walls:

- The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time, depending on temperature.
- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster.
- Level out imperfections of the internal support with filler-pasta ready to use RASAN STUCCO or with powdered filler STUCCO 3 STELLE.
- Use the sandpaper in order to remove surface irregularities and then eliminate dust deposits.
- Make sure the surface is dry and apply 1 coat of SCIK BONIFIKinsulation (anti-mold fixative) or SCIK ACRIL BONIFIK (super concentrated fixative to be thinned up with 12 Lt of water per 1Ltof product).
- Proceed applying two coats of H-SAN A NATURE SEMIGLOSS with brush,roller or spray which has to be thinned up with water in the following percentages: 1st coat: approx.25-30% ; 2nd coat: approx. 20-25%.

Old Walls:

- The surface to be treated must be dry.
- Scrape off any loose flaking and poorly adhering coating, scraping and washing the surface with plenty of wateror using a pressure washer.
- Proceed following the instruction of 'NEW WALLS' from the third point onwards (filler application).


DECORAZIONI RIVEDIL S.r.l.

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 03937370751

www.rivedil.com - export@rivedil.com

TECHNICAL DATA	
Nature of the bond	Acrylic resin in water dispersion
Viscosity	
Drying Time	12-24 h complete.
Thinning	10-15%
Yield	10-12m ² /Lt
Specific weight	1,29Kg/Lt
Colors	See HSAN chart
Dry aspect	Semigloss effect
Wet aspect	liquid
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	μGr/m ³
TVOC	30μGr/m ³
PH	7-8°C
Cleaning	Water
Packing	5LT,15LT
CHARACTERISICS	
Characteristics:	Environmentally friendly.
Can be applied on:	Walls,Wood.
for:	Interiors.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Roller,Brush.
Related products:	DECOR FONDO.

CAUTION:

- N.4 The raw materials used are natural and may have minor differences depending on the lots used. It is therefore recommended to use the same batch of product for the same work to be carried out. If this is not possible, mix the batches together.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.

DECORAZIONI RIVEDIL S.r.l.

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 03937370751

www.rivedil.com - export@rivedil.com