

SCHEDA TECNICA N°38



DESCRIPTION

ANTIFER is an anti-rust primer based on modified alkyd resins, for ferrous metal surfaces.

The product is endowed with an excellent anti-corrosive power due to the special pigments of which it is composed.

ANTIFER is easy to apply, ensuring a perfect adhesion to the surface, excellent distension and elasticity.

ANTIFER ia availaible in red, grey and black version.

APPLICATION Unpainted ferrous metal surfaces: Brush or wash the surface, in order to remove any foil flakes not perfectly anchored and ensure that any rust traces are cleaned up. Degrease the support with DILUENTE NITRO, if necessary. Proceed applying with brush or spray 2 coats of anti-rust ANTIFER, which has to be thinned up with ACQUA RAGIA or DILUENTE SINTETICO in the following percentages: 1st and 2nd coat: approx. 10-15% Pre-painted ferrous metal surfaces: Remove any layers of old and flaky paint or imperfectly anchored parts. Manually remove the rust. Roughen the support for a better anchorage. Dust the surface. Proceed as for the 'Unpainted ferrous metal surfaces' from the third point onwards.



TECHNICAL DATA	
Nature of the bond	Modified alkyd resins
Viscosity	
Drying Time	2- h at touch, 12-24 h complete.
Thinning	Water ragia diluente sintetico 10-15%
Yield	8-10m²/Lt
Specific weight	1,714Kg/Lt
Colors	Red, grey, black
Dry aspect	coloured
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	years (in sealed, unopened original packing)
VOC	µGr/m³
тиос	N/A
РН	N/A
Cleaning	Water ragia
Packing	14LT,2,5LT,0,500LT
CHARACTERISICS	
Characterisics:	Linea antiruggini.
Can be applied on:	
for:	Interiors ed Exteriors.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Brush,Sprayer.
Related products:	DILUENTE NITRO, DILUENTE SINTETICO, ACQUA RAGIA.

SAFETY INSTRUCTIONS:

Flammable product.Keep away from heat, sparks and open flames – No smoking. Avoid contact with skin and eyes. Avoid breathing dust/fume/gas/mist/vapours/spray.If swallowed, do NOT induce vomiting: immediately consult the doctor showing the product label or the container. Keep out of reach of children. Avoid release to the environment, as toxic. Do not empty into drains or the aquatic environment.

For further information, please consult the SSR38 safety data sheet.

ITEM SPECIFICATION:

Anti-rust for iron.

Applications to be made on already prepared surfaces of anti-rust for iron ANTIFER cod.A001 based on modified alkyd resins, in at least 2 layers, in the quantities determined by the substrate absorption.

Supply and installation of material € per sqm.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.

- In the original, sealed containers and in appropriate temperature conditions. The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.

- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge, however, being elements such as weather conditions, labor, tools, quality of third party products and others, not under the direct control of the Rivedil, this document does not constitute a warranty, nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document. We recommend that you always check the suitability of the product to each specific instance. This supersedes all previous editions.



COLORIFICIO RIVEDIL di COSIMO CODARDO Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy Tel. (+39) 0832 731293 - (+39) 0832 731273 PIVA 01122590753 www.rivedil.com - export@rivedil.com