

SCHEDA TECNICA N°43

SPART SINT

Solvent-based synthetic painting

DESCRIPTION

SPART SINT is a painting for road signs that in addition to having a very high coverage and high resistance contains a fair amount of very fine glass beads that make the product refractive.

APPLICATION

INDICATIONS OF USE:

- Make sure that the support is dry and dust-free.
- Proceed with appropriate equipment, to the application of 2 coats of SPART SINT, to be diluted with DILUENTE NITRO in the following percentages: approximately 15-20%.
- Make sure that the product is perfectly dried between one hand and the other.



TECHNICAL DATA	
Nature of the bond	Special resins and glass beads
Viscosity	
Drying Time	2 h at touch, 1-2 h complete.
Thinning	Diluente per spart sint 15-20%
Yield	15-20m²/Lt
Specific weight	N/A
Colors	White, Yellow, Black
Dry aspect	
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
voc	μGr/m³
TVOC	N/A
PH	N/A
Cleaning	Water ragia
Packing	14LT,5LT
CHARACTERISICS	
Characterisics:	Linea speciale.
Can be applied on:	
for:	Esterno.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Roller, Brush, Sprayer.
Related products:	DILUENTE PER SPART SINT.

SAFETY INSTRUCTIONS

Flammable. Keep out of flames and sparks; Do not smoke; Harmful Avoid any contact with the skin and eyes; Do not inhale gases, fumes, vapours, aerosols; In case of ingestion, do not provoke vomiting; Consult your doctor immediately and show him the container or the label; Keep away from children's reach; Toxic to the environment; Do not dispose of residues in sewers or in aquatic environments. For more information see the SSR43 Safety Data sheet.

ITEM OF SPECIFICATIONS

Synthetic solvent-based painting.

Applications, on pre-arranged surfaces, of synthetic paint with solvent SPART SINT cod. SS01 made of special resins and reflective beads, in at least 2 layers, in the quantities determined by the absorption of the support.

Supply and installation of the material €...... to the Mq.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions. The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge, however, being elements such as weather conditions, labor, tools, quality of third party products and others, not under the direct control of the Rivedil, this document does not constitute a warranty, nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document. We recommend that you always check the suitability of the product to each specific instance. This supersedes all previous editions.



Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy Tel. (+39) 0832 731293 - (+39) 0832 731273 P.IVA 01122590753