

**SCHEDA TECNICA N°101**

RASATO

Plastic coating with a shaved rustic final effect. RASATO ACRILSILOSSANICO also available

DESCRIPTION

RASATO is a plastic coating with excellent filling and masking power besides a shaved final effect, for internal and external use.

The high coating thickness created by RASATO, protects the substrate from atmospheric and polluting agents.

Furthermore this product does not cause any cracks and detachments.

Available in 3 different grain sizes:

Medium : grain size 1,5 – 2,2 mm

Fine : grain size 1 – 1,5 mm

Very Fine : grain size 0,3 – 0,5 mm

APPLICATION

New Walls:

- The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time, depending on temperature.
- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster.
- Level out imperfections of the internal support with RASAN STUCCO (check technical data sheet 48) or with K-STUKK (check technical data sheet 48a); use instead RIVENDUIT CALCE for the external support (check technical data sheet 48b). In case of holes or micro-cracks, fill the inner walls with STUCCO TRE STELLE (check technical data sheet n° 33) and the external ones with ESTERN STUCCO (check technical data sheet n°76).
- Use the sandpaper in order to remove surface irregularities and then eliminate dust deposits.
- Apply 1 coat of SCIK PURAL ACRIL insulation (check technical data sheet n°118) or FISSATIVO ACRILICO TRE STELLE (check technical data sheet n°5).
- Proceed applying the special SOTTOFONDO PER RIVESTIMENTI (check technical data sheet n°97).
- Continue with the application of 1 coat of RASATO ready to use, by spalter.

Old Walls:

- The surface to be treated must be dry.
- Scrape off any loose flaking and poorly adhering coating, scraping and washing the surface with plenty of water or using a pressure washer.
- Proceed following the instruction of 'NEW WALLS' from the third point onwards.



COLORIFICIO RIVEDIL di COSIMO CODARDO
Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy
Tel. (+39) 0832 731293 - (+39) 0832 731273
P.IVA 01122590753
www.rivedil.com - export@rivedil.com

TECHNICAL DATA

Nature of the bond	Acrylic copolymers in aqueous emulsion
Viscosity	
Drying Time	2 h at touch, 12-24 h complete.
Thinning	Ready to use
Yield	Grana grossa@3,200-3,500@grana media@2,800-3,000@grana fine@2,000-2,500@grana finissima@1,800-2,000m ² /Kg
Specific weight	N/A
Colors	Check RASATO color chart or Rivedil Color system
Dry aspect	
Wet aspect	Mellow
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	µGr/m ³
TVOC	N/A
PH	N/A
Cleaning	Water
Packing	10KG,25KG

CHARACTERISTICS

Characteristics:	Linea Rivestimenti.
Can be applied on:	Walls.
for:	Interno ed esterno.
Certifications:	

TOOLS AND RELATED PRODUCTS

Tools:	Spalter.
Related products:	RASAN STUCCO,K-STUCC,RIVENDUIT CALCE,STUCCO TRE STELLE,ESTERN STUCCO,SCI K PURAL ACRIL,FISSATIVO TRE STELLE.

SAFETY INSTRUCTIONS:

The product does not require labelling under the Decree 285 of 16/7/98 and subsequent amendments and updates. Use the product in accordance with the relevant health and safety regulations of the country. Do not dispose of the containers in the environment after use; let the residues dry and treat them as special waste. For further information please refer to **SSR101** safety data sheet.

ITEM SPECIFICATION:

Plastic coating with a shaved final effect. Applications to be made on the already prepared surfaces, for internal and external use. RASATO cod. R determined in quantities by the substrate absorption. Supply and installation of material € per sqm.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.



COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 01122590753

www.rivedil.com - export@rivedil.com