

**SCHEDA TECNICA N°126** 

# **IMPRECOLOR**

IMPRECOLOR is an anti-woodworm and fungicide impregnating agent of wooden supports

## **DESCRIPTION**

IMPRECOLOR is a coloured, woodworm and fungicide impregnating agent for the protection of wooden supports.

Its composition based on modified acrylic resins, gives the product an excellent absorbency power necessary for the protection from atmospheric agents.

IMPRECOLOR also allows to obtain filler and water repellent finishes, as it forms a microporous film highly breathable to water vapour.

IMPRECOLOR contains special absorbing additives of ultraviolet rays and is coloured with transparent pigments that colour the wood without masking its veins.

## **APPLICATION**

>strong>NEW WOOD SURFACES:

- Sand to remove any raised wood flakes.
- Clean the surface and check that the wood is not damp.
- Grouting imperfections with PASTA STUCCO. Sand the grouting and remove the dust.
- After 6-12 hours, proceed with brush, spray or immersion, to the application of 2 coats of IMPRECOLOR, ready to use.

## WOOD SURFACES ALREADY PAINTED:

- Check the condition of the old paints. Remove the peeling parts or not perfectly adherent.
- Proceed as for the new wood surfaces from second point onwards



# COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy Tel. (+39) 0832 731293 - (+39) 0832 731273 P.IVA 01122590753

www.rivedil.com - export@rivedil.com

TECHNICAL DATA	
Nature of the bond	Modified acrylic Resins
Viscosity	Woulifed act yill Nesilis
Drying Time	2 h at touch, 6-12 h complete.
Thinning	Ready to use
Yield	8-10m²/Lt
Specific weight	0,814Kg/Lt
Colors	Color Charts Linea Legno
Dry aspect	Colorful
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	years (in sealed, unopened original packing)
VOC	μGr/m³
TVOC	N/A
РН	N/A
Cleaning	Water Ragia
Packing	2,5LT,0,750LT
CHARACTERISTICS	
Characteristics:	Linea Legno.
Can be applied on:	Wood.
for:	Interiors ed Exteriors.
Certifications:	
TOOLS AND RELATED PROD	DUCTS
Tools:	Brush.
Related products:	PASTA STUCCO.

#### **SAFETY INSTRUCTIONS**

Flammable. Keep out of flames and sparks; Do not smoke; Harmful Avoid any contact with the skin and eyes; Do not inhale gases, fumes, vapors, aerosols; In case of ingestion, do not provoke vomiting; Consult your doctor immediately and show him the container or the label; Keep away from children's reach; Toxic to the environment; Do not dispose of residues in sewers or in aquatic environments. For more information see the SSR126 Safety Data sheet.

# **ITEM OF SPECIFICATIONS**

Coloured impregnating agent, anti-woodworm, fungicide for wood. Applications, on already pre-disposed surfaces, of coloured impregnating agent, anti-IMPRECOLOR is a coloured, woodworm and fungicide impregnating agent for the protection of wooden supports. Its composition based on modified acrylic resins, gives the product an excellent absorbency power necessary for the protection from atmospheric agents. IMPRECOLOR also allows to obtain filler and water repellent finishes, as it forms a microporous film highly breathable to water vapour. IMPRECOLOR contains special absorbing additives of ultraviolet rays and is coloured with transparent pigments that colour the wood without masking its veins. woodworm, based on alkyd resins and solid pigments in light, in at least 2 layers, in the quantities determined by the absorption of the support. Supply and installation of the material  $\in$  ................................ to the Mq.

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions. The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge, however, being elements such as weather conditions, labor, tools, quality of third party products and others, not under the direct control of the Rivedil, this document does not constitute a warranty, nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document. We recommend that you always check the suitability of the product to each specific instance. This supersedes all previous editions.



## COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy Tel. (+39) 0832 731293 - (+39) 0832 731273 P.IVA 01122590753

www.rivedil.com - export@rivedil.com