

**SCHEDA TECNICA N°163**

## RASANTE UNIVERSALE FIBRATO

Osmotic cement powders, acrylic resins and fibrous fillers in paste forma

### DESCRIPTION

RASANTE UNIVERSALE FIBRATO is a special paste product suitable for roof terraces for protection from atmospheric agents.

It can be applied with a brush for the protection of joints on roof terrace by diluting the product with 20% of water, if necessary, or with a spatula, ready to use, in case of smoothing the entire surface.

### APPLICATION

Make sure that the substrate is dry and free of grease, oil or dust. Remove, brushing off any granules or efflorescence present.

#### APPLICATION ON ROOF TERRACES (surface area > 3m<sup>2</sup>)

Use a fiberglass net and cover the entire surface.

Cover the roof terrace with 1 coat of RASANTE UNIVERSALE FIBRATO, ready to use, not less than 1 mm thick, taking care to cover the entire net with the product using a trowel as a tool.

#### APPLICATION ON JOINTS OF ROOF TERRACES (surface < 3m<sup>2</sup>)

Dilute the product with 20% water, taking care to mix it all with an electric mixer.

Cover with a brush the joints of the roof terrace with 1 coat of RASANTE UNIVERSALE FIBRATO.

NOTE: The toanlity of grey may vary according to different batches.



#### COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 01122590753

www.rivedil.com - export@rivedil.com

TECHNICAL DATA	
Nature of the bond	N/A
Viscosity	
Drying Time	h complete.
Thinning	
Yield	secondo spessore <sup>2</sup> /Kg
Specific weight	20Kg/Lt
Colors	Grigio cemento
Dry aspect	
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	µGr/m <sup>3</sup>
TVOC	N/A
PH	N/A
Cleaning	Water
Packing	20KG

CHARACTERISTICS	
Characteristics:	Linea restauro.
Can be applied on:	Walls,Wood,Floors solari.
for:	Esterno.
Certifications:	

TOOLS AND RELATED PRODUCTS	
Tools:	Brush,Spalter.
Related products:	.

### SAFETY INSTRUCTIONS

The product does not require labelling according to D.L. 285 of 16/7/98 and subsequent amendments and updates. Use the product according to the current hygiene and safety regulations; after use do not disperse the package in the environment; leave the residues to dry well and treat them as special waste. For further information consult the SSR Safety Data Sheet.

### SPECIFICATION ITEM

Ready-to-use compound for joints and solar floors. Applications, on already prepared surfaces, of RASANTE UNIVERSALE FIBRATO cod. RFU20, based on osmotic cement powders, acrylic resins and fibrous fillers, in 1 coat, in the quantities determined by the absorption of the substrate. Cost of supply and installation of the material per sqm.

### NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.



#### COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 01122590753

www.rivedil.com - export@rivedil.com