

**SCHEMA TECNICA N°410**

## **STILE BAROCCO TRAVERTINO**

Special decorative plaster with marble effect matt

### **DESCRIPTION**

TRAVERTINO is a decorative plaster made of lime and various natural components. Its easy to apply with a trowel and finished with fine sandpaper, and resembles ancient TRAVERTINO, the ancient Roman marble.

The product ensures maximum breathability and prevents the formation of mold and bacteria.

Ideal for exterior facades of houses or buildings.

### **APPLICATION**

- Make sure the surface is completely dry . If the surface is plastered, make sure it had a curing time of at least 28 days , depending on temperature. - Make sure that the media has been well prepared and is suitable for coating: plaster must be dry, not have any granules , on old walls, make sure that there is no poor quality or powdery paint, remove flaking paint etc. . - Apply 1 coat of SCIK PURAL ACRIL primer if necessary. -Apply with a brush or roller one or two coats of DECOR FONDO PRIMER diluted with 5-10 % water. - Apply 1 coat of Travertino with a stainless steel trowel, smoothing the surface completely. The thickness of this first coat will be ' decorated by grains of Travertine . - Once completely dry (about 24 hours), apply a 2nd coat of the product with irregular strokes and gentle pressure to smooth the surface. Sand the surface. - Prior to complete drying polish with a clean stainless steel trowel. - To achieve a shiny polish or to protect and make the surface completely washable , apply a coat of CERA D'ARTE NEUTRA or HYDROCERA NEUTRA (see data sheet ) or HYDROFINISH OPACO (MATT) for a matt finish. OUTDOOR PROTECTION: - Apply HYDRO FINISH OPACO or HYDRO FINISH SPECIAL ( see data sheet ) .

**DECORAZIONI RIVEDIL S.r.l.**

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 03937370751

[www.rivedil.com](http://www.rivedil.com) - [export@rivedil.com](mailto:export@rivedil.com)

<b>TECHNICAL DATA</b>	
Nature of the bond	mixture of resins and slaked lime
Viscosity	
Drying Time	2 h at touch, 12-24 h complete.
Thinning	Ready to use
Yield	1-1,2m <sup>2</sup> /Lt
Specific weight	1,712Kg/Lt
Colors	Bianco
Dry aspect	Ancient Roman Travertino Marble
Wet aspect	Pasty white with flecks of marble
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	10µGr/m <sup>3</sup>
TVOC	40µGr/m <sup>3</sup>
PH	11-12°C
Cleaning	Water and Soap
Packing	4LT,15LT
<b>CHARACTERISICS</b>	
Characterisics:	Breathable, Anti-mildew.
Can be applied on:	Walls, Wood.
for:	Interiors/Exteriors.
Certifications:	
<b>TOOLS AND RELATED PRODUCTS</b>	
Tools:	Stainless Steel Trowel 200x80cm, Stainless Steel Trowel 240x100cm,.
Related products:	DECOR FONDO, CERA D'ARTE NEUTRA, HYDROCERA, HYDRO FINISH OPACO.

## NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.

### DECORAZIONI RIVEDIL S.r.l.

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 03937370751

www.rivedil.com - export@rivedil.com