

TDS N°106

## **HYDRO FONDO AM**

Special primer for PATINE CALCE

## **DESCRIPTION**

HYDRO FONDO AM is a product made to be used together with PATINE CALCE decorative paint, in order to achieve the special antique effect typical of lime.

HYDRO FONDO AM can be applied on any kind of surface (plaster, drywall (plasterboard), wood), both indoors and outdoors.

**APPLICATION** · Make sure the surface is completely dry. If the surface is plastered, make sure it had a curing time of at least 28 days, depending on temperature. · Make sure the media has been well prepared and is suitable for coating: plaster must be dry, not have any granules, on old walls, make sure there is no poor quality or powdery paint, remove flaking paint etc. · Apply 1 coat of SCIK PURAL ACRIL primer if necessary. · Apply with a brush or roller one or two coats of HYDROFONDO AM diluted with 5-10% water.

TECHNICAL DATA	
Nature of the bond	Special acrylic resins dispersed in water and various additives
Viscosity	
Drying Time	2 h at touch, 6-12 h complete.
Thinning	5-10% Water
Yield	10-12m²/Lt
Specific weight	1,677Kg/Lt
Colors	White
Dry aspect	Opaque white
Wet aspect	Gelatinous white
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 Years (in sealed, unopened original packing)
voc	20μGr/m³
TVOC	N/A
РН	7-8°C
Cleaning	Water and Soap
Packing	0.750LT,4LT
CHARACTERISTICS	
Characteristics:	
Can be applied on:	Walls,Wood,Plastic.
for:	Interiors/Exteriors.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Roller,Brush.
Related products:	PATINE CALCE.

## **NOTES**

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions. The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge, however, being elements such as weather conditions, labor, tools, quality of third party products and others, not under the direct control of the Rivedil, this document does not constitute a warranty, nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document. We recommend that you always check the suitability of the product to each specific instance. This supersedes all previous editions.